

# Product Information

## Epoxy Hardener Amid A 15x70 LV

### Product Description:

Epoxy Hardener Amid A 15x70 LV is a polyamide containing, low viscosity epoxy resin curing agent in a xylene solvent. It has superb water and corrosion resistance properties. It has excellent pigment, a long pot life, dries fast and provides excellent adhesion.

### Applications:

Epoxy Hardener Amid A 15x70 LV can be used in a wide variety of epoxies including but not limited to epoxies used in coatings for marine, pool, tank, pipe and masonry surfaces. It can be used with epoxies that are used as adhesives, grouts, caulking agents and electrical potting materials.

### Specifications:

Parameters (units)	Specifications
Amine value (mg KOH / g)	160 - 240
Solvent type	Xylene
Solid content (%)	69 - 71
Viscosity, Brookfield at 25 °C (cP)	400 - 600
Color (Gardner)	< 12
Density (g/cm <sup>3</sup> )	0.94 - 0.98
Flash point (°C)	- 27
Pot-life (min)	80 - 100
Amine hydrogen equivalent weight (g/mol)	210 - 230

Bisley International LLC  
1790 Hughes Landing Boulevard Suite 400  
The Woodlands 77380 TX USA  
Phone number: +1 (844) 424 7539  
Emergency telephone number: +1 855 237 5573

[bisleyinternational.com](http://bisleyinternational.com)

Copyright 2021 Bisley & Co. Pty Ltd. All rights reserved



## Packaging:

Material is available in 180 kg drums, IBCs and in bulk. Further packaging options may be available upon enquiry.

## Storage:

The resin should be stored indoors in original, unopened, undamaged packaging in a dry place at storage temperature between 5-30 °C. Exposure to direct sunlight should be avoided. The shelf life of the resin under the mentioned storage conditions is 1 year. For further safety information refer to product SDS available from your Bisley and Company contact.

## Safety:

For further safety information refer to product SDS available from your Bisley International contact.

Disclaimer: This document is for information purposes only. Customers are responsible for testing and confirming the suitability of this product in their application. To the extent permitted by law, no warranty as to merchantability or fitness of purpose, expressed or implied, is made.

### Global Headquarters

#### Sydney, Australia

Bisley & Company  
Level 12, Tower B Citadel Towers  
799 Pacific Highway  
Chatswood NSW 2067 Australia  
Phone: +61 2 8905 4200  
Fax: +61 2 8905 4238  
Email: [australia@bisley.biz](mailto:australia@bisley.biz)

### Jakarta, Indonesia

PT Bisindo Kencana  
Puri Indah  
Financial Tower  
9<sup>th</sup> Floor, Unit 09 Jalan Puri  
Lingkar Dalam Blok  
T8 Jakarta Barat 11610  
Indonesia  
Phone: +6221 530 7287

### Bangkok, Thailand

Bisley Asia (Thailand) Co. Ltd.  
Mahatun Plaza Building 18th Floor  
888/186 Ploenchit Road  
Lumpini, Pathumwan  
Bangkok 10330  
Thailand  
Phone: +66 0 2689 6396  
Fax: +66 0 2689 6394

### Kuala Lumpur, Malaysia

Bisley Asia (M) Sdn Bhd  
Co. Reg. No.:199201002123  
(233627-U)  
Suite 20-01 & 20-02B,  
Level 20, The Pinnacle,  
Persiaran Lagoon, 47500  
Bandar Sunway, Subang Jaya Selangor,  
Malaysia  
Tel: +603-56244287/4289  
Fax: +603-56244201

### Dubai, United Arab Emirates

Bisley Chemicals Trading LLC  
1802 B2B Office Tower  
Business Bay  
PO Box 9298  
Dubai United Arab Emirates  
Phone: +971 4 3310088  
+971 4 3310111  
Fax: +971 4 3310099

### USA and Canada

Bisley International LLC  
1790 Hughes Landing Boulevard  
Suite 400  
The Woodlands 77380 TX USA  
Phone: +1 (844) 424 7539  
Emergency telephone number:  
+1 855 237 5573  
Email: [international@bisley.biz](mailto:international@bisley.biz)

Bisley International LLC  
1790 Hughes Landing Boulevard Suite 400  
The Woodlands 77380 TX USA  
Phone number: +1 (844) 424 7539  
Emergency telephone number: +1 855 237 5573

[bisleyinternational.com](http://bisleyinternational.com)

Copyright 2021 Bisley & Co. Pty Ltd. All rights reserved

