

# Product Information

## PPG 2000

### Product Description:

PPG 2000 is a very low odor and colorless viscous liquid composed of polypropylene glycol with an average molecular weight of 2000. It is a high-performance, low monomer containing polyol. It is slightly hygroscopic and may absorb water.

### Applications:

PPG 2000 is used in polyurethane and other applications, including cast elastomers, sealants, adhesives and defoamers. It is used in reaction injection molding (RIM), lubricants, plasticizers and crude oil de-emulsifiers. It is used as a surfactant, wetting agent and dispersant in leather finishing.

### CAS No. :

25322-69-4

### Specifications:

Parameters (units)	Specifications
Appearance	Colorless viscous liquid
Hydroxyl number (mg KOH/g)	54.5 - 57.5
Acid number (mg KOH/g)	≤ 0.05
Water content (%)	≤ 0.05
Viscosity, at 25 °C (mPa.s)	300 - 500
pH	5.5 - 7.5
Color (APHA)	≤ 50

\*% denoted represents wt/wt %, unless noted otherwise

Bisley International LLC  
1790 Hughes Landing Boulevard Suite 400  
The Woodlands 77380 TX USA  
Phone number: +1 (844) 424 7539  
Emergency telephone number: +1 855 237 5573

[bisleyinternational.com](http://bisleyinternational.com)

Copyright 2021 Bisley & Co. Pty Ltd. All rights reserved



## Packaging:

Material is available in 210 kg steel drums, 1000 kg IBCs, 21 MT flexitanks and 23 MT iso tanks. Further packaging options may be available upon inquiry.

## Storage:

Product should be stored at 10 - 35 °C in a dry place away from direct sunlight in sealed, original packaging. Shelf-life is 12 months if stored in sealed, moisture

## Safety:

For further safety information refer to product SDS available from your Bisley International contact.

Disclaimer: This document is for information purpose only. Customers are responsible for testing and conforming the suitability of this product in their application. To the extent permitted by law, no warranty as to merchantability or fitness of purpose, expressed or implied, is made.

### Global Headquarters

#### Sydney, Australia

Bisley & Company  
Level 12, Tower B Citadel Towers  
799 Pacific Highway  
Chatswood NSW 2067 Australia  
Phone: +61 2 8905 4200  
Fax: +61 2 8905 4238  
Email: [australia@bisley.biz](mailto:australia@bisley.biz)

### Jakarta, Indonesia

PT Bisindo Kencana  
Puri Indah  
Financial Tower  
9<sup>th</sup> Floor, Unit 09 Jalan Puri  
Lingkar Dalam Blok  
T8 Jakarta Barat 11610  
Indonesia  
Phone: +6221 530 7287

### Bangkok, Thailand

Bisley Asia (Thailand) Co. Ltd.  
Mahatun Plaza Building 18th Floor  
888/186 Ploenchit Road  
Lumpini, Pathumwan  
Bangkok 10330  
Thailand  
Phone: +66 0 2689 6396  
Fax: +66 0 2689 6394

### Kuala Lumpur, Malaysia

Bisley Asia (M) Sdn Bhd  
Co. Reg. No.:199201002123  
(233627-U)  
Suite 20-01 & 20-02B,  
Level 20, The Pinnacle,  
Persiaran Lagoon, 47500  
Bandar Sunway, Subang Jaya Selangor,  
Malaysia  
Tel: +603-56244287/4289  
Fax: +603-56244201

### Dubai, United Arab Emirates

Bisley Chemicals Trading LLC  
1802 B2B Office Tower  
Business Bay  
PO Box 9298  
Dubai United Arab Emirates  
Phone: +971 4 3310088  
+971 4 3310111  
Fax: +971 4 3310099

### USA and Canada

Bisley International LLC  
1790 Hughes Landing Boulevard  
Suite 400  
The Woodlands 77380 TX USA  
Phone: +1 (844) 424 7539  
Emergency telephone number:  
+1 855 237 5573  
Email: [international@bisley.biz](mailto:international@bisley.biz)

Bisley International LLC  
1790 Hughes Landing Boulevard Suite 400  
The Woodlands 77380 TX USA  
Phone number: +1 (844) 424 7539  
Emergency telephone number: +1 855 237 5573

[bisleyinternational.com](http://bisleyinternational.com)

Copyright 2021 Bisley & Co. Pty Ltd. All rights reserved

